























































































Product Name	Mass Tone	Tint Tone	Light Fastness Mass Tone	Light Fastness Tint Tone	Acid Resistance	Alkali Resistance	Heat Resistance in °C	Paint Application	Textile Application	Ink Application	Plastic Application
Pigment Yellow 1			7	4-5	5	5	160	R	S	N	N
Pigment Yellow 3			7	6	5	5	160	R	R	N	N
Pigment Yellow 12			4-5	3	5	5	180	R	R	R	N
Pigment Yellow 13			6	5-6	5	5	240	S	N	R	R
Pigment Yellow 14			5	4	4	4	180	N	N	R	R
Pigment Yellow 17			6	5	4	4	240	N	N	R	R
Pigment Yellow 65			7-8	6-7	5	5	160	R	S	R	N
Pigment Yellow 74 2gx			7	6	4	4	180	R	R	S	N
Pigment Yellow 74 5gx			7	6	4	4	180	R	S	R	N
Pigment Yellow 83			7	6	5	5	220	R	N	R	R
Pigment Yellow 183			8	7	5	5	280	N	N	N	R
Pigment Yellow 191			7	7	5	5	300	N	N	N	R
Pigment Yellow 191:1			8	7	6	5	300	N	N	N	R
Pigment Orange 5			7	6	5	5	200	R	R	R	N
Pigment Orange 13			7	5	5	4	220	R	R	R	R
Pigment Orange 34			6	5	4	5	180	R	S	N	R
Pigment Red 2			6-8	4-5	5	3	180	R	R	R	N
Pigment Red 3			7	5	5	5	180	R	S	N	N
Pigment Red 4			6	5	3	4	180	R	S	N	N
Pigment Red 8			6	4	5	4	180	N	R	R	N
Pigment Red 31			6	5	5	5	180	N	R	N	N
Pigment Red 32			6	5	5	4	180	N	R	N	N

Product Name	Mass Tone	Tint Tone	Light Fastness Mass Tone	Light Fastness Tint Tone	Acid Resistance	Alkali Resistance	Heat Resistance in °C	Paint Application	Textile Application	Ink Application	Plastic Application
Pigment Red 48:1			6	4	5	5	240	S	N	N	R
Pigment Red 48:2			6	4	5	5	240	R	N	R	R
Pigment Red 48:3			6	5	5	5	260	N	N	N	R
Pigment Red 48:4			6	4	5	4	180-240	R	N	N	R
Pigment Red 52:1			7	5	5	5	200	N	N	R	N
Pigment Red 53:1			5	3	3	4	180	N	N	R	R
Pigment Red 57:1			5	4	4	4	180	R	N	R	R
Pigment Red 112			7	6	5	5	180	R	R	R	N
Pigment Red 122			8	6	5	5	280	R	R	R	R
Pigment Red 146			6	5	5	5	180	N	N	R	N
Pigment Red 170 F3RK			8	7	5	5	280	R	N	R	R
Pigment Red 170 F5RK			7	6	5	5	180	R	R	R	R
Pigment Red 210			6	6	5	5	200	R	R	N	N
Pigment Blue 15:0			8	7	4	5	180	R	R	R	R
Pigment Blue 15:1			8	7	5	5	280	N	N	N	R
Pigment Blue 15:3			8	7	5	5	280	R	R	R	R
Pigment Blue 15:4			8	7	5	5	180	N	N	R	N
Pigment Green 7			8	7	5	5	280	R	R	R	R
Pigment Violet 23			8	7	5	5	280	R	R	R	R
Pigment Violet 3			5	4	4	3	160	N	N	R	N
Pigment Violet 27			5	4	3	4	160	R	N	N	N

**R** - Recommended  
**S** - Suitable  
**N** - Not Suitable

**Light Fastness** : 1 to 8, 8 = Excellent

**Acid and Alkali Resistance** : 1 to 5, 5 = Excellent

**Color Reproduction** : For technical reasons connected with color reproduction, the colors shown may not exactly match the pigment colors and do not represent a particular finish.



## Intermediate Product List

---

- Beta Naphthol
- Bon Acid
- AAA
- AAOA
- AAOT
- AAOCA
- AAMX
- PMP
- PTMP
- 2B Acid
- 4B Acid (Technical)
- 4B Acid (Pure)
- H Acid

- J Acid
- K Acid
- Tobias Acid
- C Acid
- PNA
- OCPNA
- Naphthol AS
- Naphthol AS-D
- Naphthol AS-E
- Naphthol AS-BS
- Naphthol AS- PH
- Naphthol AS-IRG
- Naphthol AS -LC

- Naphthol AS -BO
- Naphthol AS-OL
- Fast Scarlet G base
- Fast Red B base
- MNPT
- Fast Blue B Base
- Fast Bordeaux GP base
- Fast Orange GC Base
- Fast Red KD Base
- Fast Scarlet R Base
- Red RI Base
- Fast Scarlet RC Base



M: +91-9327006322, +91-8000245827  
D/167, 1st Floor, B.G. Towers, Shahibaug Road,  
O/s Delhi Gate, Ahmedabad-380004.  
Email : chandresh@neeljyotchemicals.com,  
yash@neeljyotchemicals.com  
Website : www.neeljyotchemicals.com